

FINAL YEAR PROJECT REPORT
BACHELOR ENGINEERING (HONS)
(MECHANICAL ENGINEERING)
MARA INSTITUTE OF TECHNOLOGY
SHAH ALAM

TITLE :
THE ENVIRONMENTAL DEGRADATION OF ADHESIVE JOINT

MUHAZLI BIN MUHAMAD	(96387660)
ROSLI BIN YUSOF	(96624474)

MAY 1999

PREFACE

The main objectives of this project are:

1. To find the effect of environment to the adhesive joint under various condition. These conditions are:
 - Normal condition
 - Sun light condition
 - Sea water condition
 - Under ground condition
 - Normal water condition
2. To study the strength of adhesive under various conditions for different duration.
3. To monitor the mechanism of adhesive after tensile test.

CONTENT		page
	PREFACE	i
	ACKNOWLEDGMENT	ii
1.0	INTRODUCTION	1
2.0	THEORY OF ADHESIVE	3
2.1	BACKGROUND OF ADHESIVE	3
2.2	THE CLASSIFICATION OF ADHESIVE	3
2.2.1	Bonding Temperature	3
2.2.2	Origin	4
2.2.3	Method of Bonding	4
2.2.4	Structural and Nonstructural Adhesive	4
2.2.5	Permanence	5
2.2.6	Other system	5
2.3	ADVANTAGES AND DISADVANTAGES OF ADHESIVE BONDING	6
2.31	Advantages	6
2.32	Disadvantages	7
2.4	SELECTION OF JOINT DESIGN	8
2.5	SELECTION OF ADHESIVE	9
2.6	ADHESIVE MATERIAL AND PROPERTIES	10
2.6.1	Thermoplastic Adhesive	10
2.6.2	Thermosetting Adhesive	10
3.0	THEORY OF PVC	11
3.1	INTRODUCTION	11
3.2	STRUCTURE AND DEGRADATION OF POLYVINYL CHLORIDE	12
4.0	KINETIC AND MECHANISM OF ENVIRONMENTAL ATTACK	21
4.1	INTRODUCTION	21
4.2	KINETIC OF WATER ENTRY	22
4.3	EFFECT OF WATER ON ADHESIVE	25
4.3.1	Plasticisation and Swelling	25
4.3.2	Water-induced Chemical And Physical Ageing	27

4.4	EFFECT OF WATER ON THE INTERFACE	28
4.4.1	Absorption theory of adhesion and displacement of adhesive by water	28
4.5	EFFECT OF STRESS	31
4.6	EFFECT OF TEMPERATURE	31
4.8	EFFECT OF RADIATION	32
5.0	EXPERIMENTATION	33
5.1	PREPARATION OF SPECIMENS	34
5.1.1	Cutting process	34
5.1.2	Joining process	36
5.1.3	Conditioning	36
5.2	METHOD OF TESTING	37
6.0	RESULT	38
6.1	DESCRIPTION OF CODES	38
6.2	DURATION OF SPECIMEN	38
6.3	SUMARY DATA OF TESTING RESULT	39
6.3.1	Normal condition	39
6.3.2	Sunlight condition	40
6.3.3	Sea water condition	41
6.3.4	Under ground condition	42
6.3.5	Normal water condition	43
6.4	DATA ANALYSIS	44
7.0	DISCUSSION	107
7.1	TENSILE TEST	107
7.2	OVERALL DISCUSSION	114
8.0	CONCLUSION	116
9.0	RECOMMENDATIONS	118
10.0	REFERENCES	119
11.0	APPENDIX	121

1.0 INTRODUCTION

Adhesive joints are expected to retain a significant proportion of their load bearing capacity for the entire duration of the service life of the bonded structure. However, service conditions can often involve exposure to combinations of static or fatigue load and hostile environment (marine, hot/wet, weathering or chemical). It is therefore essential that the end user and the adhesive manufacture possess the necessary tools for selecting and characterising an adhesive system, to ensure reliability bond performance under hostile operating condition. Optimising joint performance requires an understanding on the failure mechanisms involved in environment degradation, and validated test methods and design methodologies suitable for predicting material degradation and life expectancy.

The general consensus is that wider used of adhesive technology has been impeded by a lack of reliable test methods, accelerated ageing procedures, quantitative data and predictive analysis for determining durability of structural adhesive joints to hostile environments.

User or designers must often expend considerable effort in selecting adhesive system and optimising process variables to maximise long term strength retention under hostile environments. The bonding process will often be determined by recommendation from the adhesive manufacturer, from previous experience or by an extensive range of durability test. Often, little or no attention is directed towards understanding the critical variables in the bonding process and their effect on the survival of the adhesive joint under the combined effects of environment and stress. The synergism of stress and